

Teak Life Natural Weathering: Extends the life of teak decks by protecting against moisture and darkening, improving dimensional stability and allowing wood to weather to a beautiful silver grey. Wears gently for enhanced beauty and long term performance.

FEATURES

- Extends the life of teak decks
- Prevents darkening
- Reduces maintenance
- Protects against discoloration
- Reduces moisture absorption

FORMULAS

Teak Life Natural Weathering is a single formula product that can be applied to previously untreated weathered wood, cleaned wood or new wood surfaces. Teak Life Natural Weathering will extend the life of your deck and improve the surface condition of the wood.



CHARACTERISTICS

- Appearance Hazy white
- Coloring Clear
- Odor Low (Slight Amine)
- Form Liquid
- Specific Gravity 1.02
- Density 8.3
- pH, (approx) 9-9.5
- Viscosity, Brookfield #1, 60RPM, 20°C (68°F) 5-6cPs
- Solvents None
- Freezing Point -1°C (31°F)
- Diluent Water
- Cleanup Water
- Drying Time @ 20°C (68°F) 48 Hours
- Drying Time (Between applications @ 20°C (68°F)) 2 Hrs.
- Coverage, pending to penetration 100 sq ft (9.29 M2) per litre
- Longer drying time needed in high humidity or low temperature
- Keep from freezing
- VOC (g/L) <5g/L

PACKAGING

- Quarts and 2.5 L cans


PREPARATION

PREPARATION IS KEY TO A SUCCESSFUL PROJECT

- Inspect the entire surface for defects and deterioration. Repair and replace defects where necessary.
- Ensure caulked seams are level with the teak deck surface and that the deck surface is even with no low or raised areas.



GENTLY WASH DECK WITH WOOD WASH



REPLACE CAULKING IN AREAS WHERE NEEDED WITH TEAK JAMMER

- Check deck for areas that hold moisture longer and resist drying; replace seam caulking in these areas with Teak Jammer.
- Gently wash the deck using Teak Life Wood Wash.
- Allow wood to dry thoroughly.
- Sand the surface with a variable speed random orbital sander using 60 grit sandpaper to create an even, level surface.
- Test formula on an inconspicuous wood surface to ensure proper color and penetration.
- Protect fiberglass, metal, brightwork and other surfaces that may come in contact with Teak Life.
- Apply a generous coat of Teak Life Natural Weathering to dry wood out of direct sunlight for optimum penetration. Apply carefully to avoid staining other surfaces.
- Apply in proper conditions with an ideal temperature of 21°C (70°F) and relative humidity of approximately 50%.
- Do not apply if rain or near-freezing temperatures are likely to occur within 24 hours after application.
- Apply generously to the point of refusal using a Corona-type China bristle brush to a consistent wet film depth of 4-5 wet mils
- Allow to dry for 2 hours in proper drying conditions.
- For enhanced protection, apply a second coat of Teak Life Natural Weathering to a consistent wet film depth of 3-4 wet mils in proper conditions. Allow 24 hours to dry.
- Always read published directions for use prior to beginning a project.

TEAK LIFE





UNTREATED



UV NATURAL WEATHERING

COVERAGE

On average, one litre will cover approximately 100 sq ft (9.29 M2) on each application, depending upon the surface condition of the wood.

CLEAN UP

Use soap and water to clean hands and tools.

MAINTENANCE

Regular maintenance will significantly enhance the long term performance of teak decks. Apply a maintenance coat of Teak Life Natural Weathering annually or when the wood surface shows any signs of fading or wear.

STORAGE

Store at a temperature of between 10°C–30°C (50°F–86°F) in dry place. Keep containers tightly closed.

SAFETY

Do not allow to freeze. KEEP OUT OF REACH OF CHILDREN. Avoid breathing vapors or mist. Use only in areas with adequate ventilation. Wear an appropriate, properly fitted NIOSH approved respirator. If swallowed, call a poison control center or doctor immediately. For eye contact, flush immediately with water for at least 15 minutes and call a doctor. For skin contact, wash with soap and water. Remove and wash contaminated clothing. Consult a doctor if any irritation persists.

CONDITIONS OF SALE

The only obligation of the manufacturer and seller shall be to replace such quantity of Teak Life product that is proven to be defective. Proof of purchase is required. Seller or manufacturer shall not be liable for any loss or damage connected with the use and/or handling of this product. All labor costs are specifically excluded. User should determine suitability of product for the intended use before application. User assumes all risk and liability in connection therewith. This warranty is expressly made in lieu of any and all other rights, warranties, conditions and remedies, express or implied, including but not limited to any implied warranty or condition of merchantability, fitness for a particular purpose, and any warranty or condition arising out of a course of dealing, a custom or usage of trade. If any distributor or seller of product offers warranties or remedies which differ from those offered by Teak Life, Teak Life accepts no responsibilities for such warranties or remedies.